

## PU2060 SELF-SMOOTHING FLOOR

### Chemical resistance list for Arturo PU2060 Self-smoothing Floor

Chemicals	%	Arturo PU2060
<b>Mineral acid</b>		
1. Phosphoric acid	10	X
2. Phosphoric acid	> 10	X
3. Nitric acid	10	X
4. Concentrated Nitric acid	> 10	X/X
5. Hydrochloric acid	20	X
6. Hydrochloric acid	> 20	X/X
7. Sulfuric acid	10	X
8. Sulfuric acid	30	X/X
9. Sulfuric acid	> 30	X/X
<b>Organic acid</b>		
1. Acetic acid	10	X
2. Acetic acid	> 10	-
3. Lactic acid	5	X
4. Formic acid	5	X
5. Formic acid	> 5	X/X
<b>Alcaline solutions</b>		
1. Natron-/Potassium hydroxide	10	X
2. Natron-/Potassium hydroxide	50	X
3. Ammonia	10	-
4. Ammonia	25	-
<b>Solvents</b>		
1. Petrol		X
2. White spirit		X
3. Toluene		-
4. Xylene		-
5. Benzene		-
6. Methanol		-
7. N-butanol		-
8. Ethanol	30	X
9. Acetone		-
10. Perchloroethylene		-
11. Carbon tetrachloride		-
12. Trichloroethylene		-
13. Heptane		X
14. Kerosene		X
<b>Oils and fats</b>		
1. Vegetable oils		X
2. Animal fats		X
3. Diesel fuel		X
4. Sump oil		X
5. Cardan oil		X

# EP2060 SELF-SMOOTHING FLOOR

Chemicals	%	Arturo PU2060
<b>Various</b>		
1. Vegetable and fruit juices		X
2. Beer		X
3. Wine		X
4. Hydrogen peroxide	10	X
5. Salts (in general)		X

The tests were carried out over a period of 7 days at 20°C.

- X Resistant.
- X/X Resistant against spilling
- Not resistant.

Uzin Utz Nederland bv operates the quality assurance system in accordance with NEN-EN ISO-9001/14001 and is certified for this by TÜV Nederland QA. This means that deliveries are made in accordance with the product and process specifications drawn up for this system. Products and services supplied by Uzin Utz Nederland bv also comply with the description in these technical specifications. As different site conditions and working practices are unknown, Uzin Utz Nederland bv accepts no liability for any damage resulting from any use of its products. With the publication of this data sheet, all previously published data sheets concerning this product become invalid. © Uzin Utz Nederland bv. All rights reserved. Copying and/or reproduction of this publication, in whatever form, is not permitted without the written permission of Uzin Utz Nederland bv. | 03.2020