

Adhesive for folder-gluing machines

# UZIN PAPER-BECK

Water dispersion adhesive for applications by spaying

## Applications:

Industrial use adhesive, plasticizer-free, consisting of vinyl acetate and ethylene dispersion for manual paper packaging applications like paper lamination and several types of simple adhesions. Exhibits good adhesion to various paper surfaces and leaves permanently flexible adhesive joints. Suitable for side seams of paper bags.

Suitable for / on:

- ▶ Several types of ink or varnish printed paper and its derivatives
- ▶ All types of carton and its derivatives
- ▶ Various plastic surfaces non electrically treated (corona)

## Product properties / advantages:

Water dispersion adhesive of vinyl acetate and ethylene, with high content to active solids. Dries fast and develops high strength at early drying stages. Suitable for spray application by nozzle at folding-gluer machines operating at high speeds.

- ▶ Fast adhesion
- ▶ Does not “wrinkle” paper
- ▶ Permanently flexible adhesive joints
- ▶ High cohesion

## Technical Data:

Packaging:	PE container
Sizing:	30kg
Hazard:	-
Active solids:	38 - 42% (DIN EN ISO 3251)
Color:	Milky/Opaque
Density:	approx. 1,07 g/cm <sup>3</sup> (DIN EN ISO 2811-3)
Application Temperature:	approx. 0 °C (DIN ISO 2115)
Consumption:	Depends on application method
Viscosity:	2000 - 2800 mPa.s (DIN EN ISO 2555)
pH:	4,0 - 5,0 (DIN/ISO 976)
FDA approval:	-
Storage:	Min. 6 months at cold and dry place ~20°C
Cleaning:	Wet film: cold water Dry film: hot water and/or detergent Stains/Pillages: UZIN OFFSET 395

\* At 20 °C and R.H.65%.

# UZIN PAPER-BECK

## Substrate preparation:

The bonding surfaces must be dry, clean and free from dust and other substances that could impair adhesion.

Refer to safety data sheets of the product and study carefully the compatibility of each component with UZIN Hellas various products.

## Application:

1. Place the container of adhesive indoor and let it be acclimatized, for 1-2 hours.
2. Ambient temperature and humidity must be in permissible limits. Ideal temperature conditions of application ranging by 18°C to 25°C. Do not apply adhesive at temperatures below 0°C and relative humidity greater than 60%.
3. Stir well the adhesive prior to application in order to homogenize well.
4. Manual application: Apply the adhesive evenly on the surfaces to be bonded with a brush or roller.
5. Mechanical roller application: Keep always clean the feeder bowl.
6. *Any dilution of the adhesive results in physical changes of the adhesion behavior: drying time, final adhesion strength, viscosity etc.* Even though in case of dilution: use clean water to a maximum percentage 10% w/w. Always use a different clean container for the dilution and never use the initial adhesive container. Caution! Water contains Dilution water contains microorganisms, thus in a long stay in the container they are incubated and affecting biologically the adhesive, resulting to mold, or other unpleasant odors.
7. Always close tightly lids of the containers in order to prevent of moisture loss and infections.
8. Clean tools and residues while still fresh. After hardening, residues could be removed by special solvent UZIN OFFSET 395.

## Consumption:

Consumption estimation
80-120 gr/m <sup>2</sup> Depending on each substrate absorption

## Important Notes:

- ▶ Shelf life minimum 6 months when stored in a cool dry place in original packaging. Protect from frost and heat. Opened containers must be used quickly.
- ▶ Always carry out preliminary tests with all materials together, due to seldom discoloration phenomena of adhesion application onto unstable ink/varnish substrates.

## Protection of the workplace and the environment:

P101 If medical advice is needed, have product container or label at hand. P102 Keep out of reach of children. P501 Dispose of the contents/containers in accordance with the current legislation on waste treatment.

EUH208 Contains 1,2-benzisothiazol-3(2H)-one, Reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1). May produce an allergic reaction. EUH210 Safety data sheet available on request.

Maximum V.O.C. content: 0 g/L (20 °C).

**Information for persons with allergies is available at Poison center +30 210 7793777 (Greece).**

## Disposal:

Collect product residues wherever possible and reuse. Do not allow to enter the sewer system, bodies of water or the soil. Plastic containers emptied or scraped clean and no longer dripping from any residues can be recycled. Containers with liquid residues as well as collected liquid product residues are special waste. Containers with cured residues are construction / domestic waste.